


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G02B 6/12	A1	(11) International Publication Number: WO 99/09439 (43) International Publication Date: 25 February 1999 (25.02.99)
(21) International Application Number: PCT/GB98/02462 (22) International Filing Date: 18 August 1998 (18.08.98) (30) Priority Data: 9717407.2 18 August 1997 (18.08.97) GB (71) Applicant (for all designated States except US): ISIS INNOVATION LIMITED [GB/GB]; 2 South Parks Road, Oxford OX1 3UB (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): TURBERFIELD, Andrew, Jonathan [GB/GB]; 29 Derwent Avenue, Headington, Oxfordshire OX3 0AR (GB). DENNING, Robert, Gordon [GB/GB]; 26 The Row, Tootbaldon, Oxfordshire OX44 9NE (GB). (74) Agent: PERKINS, Sarah; Stevens, Hewlett & Perkins, 1 Serjeants' Inn, Fleet Street, London EC4Y 1LL (GB).		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.
(54) Title: PHOTONIC CRYSTAL MATERIALS AND A METHDO OF PREPARATION THEREOF (57) Abstract <p>The photonic crystal material has a 3-D periodic structure with a periodicity that varies on a length scale comparable to the wavelength of electromagnetic radiation. The 3-D periodic structure is produced by irradiating photosensitive material with electromagnetic radiation such that interference between radiation propagating in different directions within the sample gives rise to a 3-D periodic variation in intensity within the sample. Thereafter the irradiated material is developed to remove the less or more irradiated regions of the material to produce a structure having 3-D periodicity in the refractive index of the composite material. 3-D photonic material is particularly suited to use as low-loss waveguides and as a control with lasers to limit the number of modes into which a laser may emit radiation.</p> 		

AP5

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PHOTONIC CRYSTAL MATERIALS AND A METHOD OF PREPARATION THEREOF

The present invention relates to photonic crystal materials (also
5 known as photonic bandgap materials) and a method of preparation
thereof. In general a photonic crystal is a composite dielectric medium
having a structure which varies periodically on a length scale comparable
to the wavelength of electromagnetic radiation. In an ideal photonic crystal
multiple scattering and interference of electromagnetic waves propagating
10 through the medium results in forbidden frequency bands for a given
direction of propagation within which no propagating electromagnetic
modes exist. Within a forbidden band the material is highly reflective and
inside the medium emission of radiation having frequencies in the forbidden
band is suppressed. A photonic crystal structure may be employed to
15 modify the interaction of a material with electromagnetic radiation, including
for the purpose of controlling the appearance of the surface of the material,
and in the construction of optical and optoelectronic devices (not restricted
to visible optical frequencies).

In US 5385114 a method of preparing a photonic crystal is described
20 in which the pores of a reticulated mesh are impregnated with a suitable
liquid dielectric material which is then solidified. In order to introduce the
dielectric material, the material of the mesh must have a much higher
melting point than the dielectric material and so, for example, the material
of the mesh is a metal. Thereafter, the mesh is dissolved using a suitable
25 liquid chemical reactant to leave a porous dielectric material. The pores of
the dielectric material have a different refractive index to the material itself,
so a periodic structure made in this way would enable the material to
function as a photonic crystal. After the reticulated mesh has been
removed, the pores in the dielectric material may be filled with a separate
30 material that has a refractive index different to the refractive index of the
dielectric material. In this document the method of pore filling is
demonstrated using a random rather than a periodic metallic mesh but it is

envisaged that a periodic metal mesh could be formed by freezing electro-hydrodynamically generated metal droplets, by weaving a mesh of wires, by assembling small pieces or, by inference from the preamble, by drilling or reactive ion etching a slab of metal through a mask.

- 5 In order for the photonic crystal to be useful, the periodicity of the dielectric material must be of size comparable to the electromagnetic wavelength of interest. On a scale comparable to visible optical or near-infrared wavelengths only the etching procedures are practicable. However, fabrication of masks suitable for use in such drilling or ion etching
10 operations is extremely difficult and costly. Such techniques currently cannot provide the necessary resolution or drilling depth to produce photonic crystals for use at visible optical wavelengths.

 The present invention seeks to provide a novel photonic crystal material and a method of preparing the same, having a three-dimensional
15 periodicity with a length scale comparable to infra-red, visible, optical or shorter electromagnetic wavelengths, which overcomes the disadvantages of the known procedures described above. Reference to three dimensional periodicity is intended as reference to periodic variation of a characteristic in all three dimensions of the material. Reference to periodicity or periodic
20 variations should be taken to include the cases in which the variation is substantially periodic and cases in which two or more periodic patterns, with unit cells which may not be commensurable, are superimposed. Reference to the length scale of a periodic variation is intended to refer to a characteristic dimension of a Wigner-Seitz primitive unit cell.

- 25 The present invention provides a method of forming a photonic crystal material comprising irradiating a sample of photosensitive material with electromagnetic radiation such that interference between radiation propagating in different directions within the sample gives rise to a three dimensional periodic variation of the intensity of irradiation within the
30 sample whereby the periodic variation in intensity produces a corresponding periodic variation in the refractive index of the photosensitive material.

Ideally, the irradiated sample of photosensitive material is developed to remove either more irradiated or less irradiated regions of the sample.

To maintain the three dimensional periodicity within the sample, the intensity interference pattern is not substantially perturbed by photoinduced
5 changes in the refractive index of the sample material. The sample of photosensitive material may be subjected to multiple exposures each producing respective interference patterns within the sample.

The sample of photosensitive material may be irradiated with a coherent or partially coherent source of electromagnetic radiation. Material
10 may be introduced into the voids in the composite material or the composite material may be used as a template for the production of other composite materials having periodic variations in refractive index. By both of these techniques the optical properties of the photonic crystal material may be altered and the frequency ranges of the forbidden photonic band
15 gaps adjusted. In particular, by selection of a material having an appropriate refractive index, the overlap between forbidden frequency bands corresponding to different directions of propagation of radiation may be increased to create or to widen a complete photonic band gap, i.e. a range of frequencies for which no propagating electromagnetic modes exist
20 in any direction.

Preferably, the three dimensional pattern within the sample is formed by directing electromagnetic radiation from at least four coherent or partially coherent beams or sources at the sample of photosensitive material so as to intersect and interfere within the sample. Additionally,
25 the sample may be irradiated more than once to generate a plurality of three dimensional patterns in the sample.

With the present invention the length scale of the periodicity within the sample of photosensitive material is dependent on the length scale of the periodicity of the interference pattern which in turn is dependent on the
30 frequency of the incident radiation, on the refractive index of the photosensitive material and on the shape and direction of propagation of the interfering electromagnetic wavefronts within the sample. Three-

dimensional periodicity with a submicron length scale can be produced in the sample without the need for expensive masks making the invention particularly suitable for the production of photonic crystal material for use in optical and electro-optical applications in the infra-red, visible optical or
5 shorter wavelength regions of the electromagnetic spectrum.

Moreover, with the present invention a photonic crystal material is provided that has three dimensional periodicity of its refractive index for a thickness for at least 10 microns and more preferably at least 50 microns.

For a better understanding of the present invention, embodiments of
10 the present invention will now be described, by way of example only with reference to the accompanying drawings, in which:

Figure 1 is a diagram of a body-centred cubic (bcc) reciprocal lattice of a face-centred cubic (fcc) structure;

Figure 2 is a diagram of the threshold intensity contours resulting
15 from a single irradiation by four intersecting beams;

Figure 3 is a diagram of the same interference pattern as for Figure 2 but with a higher threshold intensity contour;

Figure 4 is a diagram of the threshold intensity contours for a double pulse exposure using different beam wavevectors to those of Figures 2 and
20 3;

Figures 5a and 5b are atomic force microscopy pictures of the top and bottom of a sample, irradiated using the method of the present invention, showing the coherence of a 3-D fcc optical pattern;

Figure 6a is an atomic force microscopy picture of the cross-section
25 of a cleaved sample, irradiated using the method of the present invention, showing fractures along terraces in the sample;

Figure 6b is a graphical representation of the cleaved sample of Figure 6a, showing the dimensions of the terraces through part of the sample; and

30 Figure 7 is a graphical representation of Bragg diffraction from a sample, irradiated using the method of the present invention, showing reflections from a 3-D fcc periodic structure.

- If a photosensitive material is simultaneously exposed to electromagnetic radiation from a plurality of coherent or partially coherent sources, an interference pattern is generated within the photosensitive material and the intensity of the irradiation or dose within the material, which is determined by the interference pattern, varies periodically. Irradiation of the photosensitive material produces changes in the refractive index of the material. In this way by generating an interference pattern of the incident radiation within the sample material a corresponding pattern of variations in refractive index is produced. The changes in refractive index produced by irradiation are small and so to increase the difference in refractive index between regions of high radiation intensity exposure and low radiation intensity exposure within the irradiated sample, the irradiated sample is preferably developed using conventional chemical processes. During development of the irradiated material regions of the material which correspond approximately to those that have absorbed less than or more than a critical dose of radiation are dissolved away. After development a periodic structure remains consisting of residual material and voids (which may be filled with other material, for example air or a solvent having a different refractive index).
- A three dimensional structure can be obtained by use of at least four interfering beams of substantially collimated and monochromatic electromagnetic radiation with differences between the individual wavevectors of each beam determining reciprocal lattice vectors and thus the symmetry of the resultant periodic structure.
- To assist in an understanding of the relationship between the wavevectors of the beams and the translational symmetry of the resultant interference pattern, the following is an explanation of the manner in which one particular set of suitable wavevectors are determined for a periodic structure having face centred cubic (fcc) symmetry. Figure 1 shows a body centred cubic (bcc) reciprocal lattice of a fcc structure with $\mathbf{a}_1 = (2\pi/d)(-1, 1, 1)$, $\mathbf{a}_2 = (2\pi/d)(1, -1, 1)$ and $\mathbf{a}_3 = (2\pi/d)(1, 1, -1)$ as a set of primitive reciprocal lattice vectors, in which d is the side of the fcc cubic unit

cell. One of the incident beams is defined to have the reference wavevector $\mathbf{k}_0 = 2\pi/d(3/2, 3/2, 3/2)$ and the wavevectors for the other three beams are then given by $\mathbf{k}_1 = \mathbf{k}_0 - \mathbf{a}_1$, $\mathbf{k}_2 = \mathbf{k}_0 - \mathbf{a}_2$ and $\mathbf{k}_3 = \mathbf{k}_0 - \mathbf{a}_3$. Differences between these wavevectors join lattice points in the bcc reciprocal lattice.

- 5 Interference of radiation with these four wavevectors will generate an interference pattern with fcc symmetry.

The following is an example of a method of producing a photonic crystal material having three dimensional periodicity. A negative photoresist, whose solubility in an appropriate solvent is decreased after
10 exposure to radiation with a wavelength of 355nm, is simultaneously irradiated by four laser beams at a wavelength of 355nm from a frequency-tripled Nd:YAG laser, having the wavevectors described above, which intersect within a layer of the photoresist. The interference of the four beams generates a three dimensional periodic intensity modulation within
15 the photoresist having fcc structural symmetry with a cubic unit cell size of approximately 0.6 μm . Figure 2 is a diagram of a resultant contour of constant intensity with Figure 3 showing a higher intensity contour within the same interference pattern. After development of the polymer, which results in removal of less-irradiated regions of the material, a three
20 dimensional periodic structure consisting of interpenetrating networks of irradiated photoresist and of air- or solvent-filled voids is formed.

Although the intensity of radiation in any interference pattern generally changes slowly on the length scale of the wavelength, the resulting structures shown in the accompanying Figures have relatively
25 sharply defined surfaces. This is achieved as a result of non-linearity in the photochemical reactions and subsequent development that produce a threshold dividing soluble and insoluble material. This threshold may correspond approximately to a contour of constant irradiation dose. Through appropriate selection of the threshold intensity, the fraction of
30 material removed from the sample may be controlled.

For any three dimensional structure produced by the method described above or any other method employing the formation of 3-D

interference patterns in the sample material, it is important that the interference pattern is such that the material to be removed during development forms a connected network. This ensures that such material can be removed from the residual material to produce voids. In addition, 5 the interconnection of the voids enables a material having a different refractive index with respect to the photosensitive material or other desirable properties to be introduced into the voids. It is also important that removing material from the voids does not destroy the periodic structure of the residual material: for example this may be achieved by ensuring that 10 the interference pattern is such that the material to be removed and the material to be retained during development both form continuous interpenetrating networks. This condition is satisfied in the example given above where the surface dividing material that is removed and residual material that is retained during development corresponds approximately to 15 the contour of constant irradiation shown in Figure 2.

Unlike the situation described above, to ensure that the periodic structure of residual material in a disconnected network is not destroyed during development, the residual material may include a permanent support structure. For example, a continuous secondary network of 20 material that permeates the photosensitive material before exposure and is not destroyed by exposure or development can support the residual material. An example of such a secondary network is a silica gel. Alternatively, the residual material may form a three dimensional periodic structure after development if isolated particles of the residual material are 25 compacted together, without destroying three-dimensional periodicity, to form a continuously connected material with a smaller unit cell than the original interference pattern.

In the above example a single exposure using four simultaneously intersecting laser beams is employed. However, this can provide only a 30 restricted class of continuously connected three dimensional structures. Greater flexibility is achieved using a double or multiple exposure technique that gives more control of the spatial distribution of the irradiation dose

within the photosensitive material. In the double exposure technique the photosensitive material is exposed twice; each exposure is such that the irradiation dose due to each exposure varies periodically with position in the photosensitive material as described above. Radiation which is
5 considered to form part of one exposure may be present in the sample at the same time as radiation considered to form part of the other; the characteristic of a double exposure, and the criterion used to assign radiation energy to one or other exposure, is that the effect of interference between radiation from different exposures in determining the spatial
10 variation of the total irradiation dose is reduced or eliminated with respect to the effect of interference between radiation from different sources belonging to the same exposure. This is achieved either by ensuring that the degree of coherence between radiation from the two exposures is less than the degree of coherence between radiation from different sources
15 belonging to the same exposure or by reducing the overlap in time between the two exposures.

Thus, using the double exposure technique, radiation in the first and second exposures can be derived from mutually incoherent sources, which may be for example the output of a laser at different times, different lasers,
20 or sources with different frequencies.

With an alternative method employing the double exposure technique, two pulses of electromagnetic radiation are used in which interference between the two pulses is reduced or eliminated by ensuring that the second pulse arrives later than the first. For example, a single laser
25 pulse is split into two pulses the second delayed in time relative to the first. The first pulse is split into four beams that are used to create an initial three dimensional interference pattern in the photosensitive material. After the first pulse has decayed, during which time the second pulse has followed a delay line, the second pulse is similarly split into four beams which follow
30 different paths from the four beams in the first exposure and overlap to form a different three dimensional interference pattern in the photosensitive material. Alternatively, the beams derived from the second pulse may

follow substantially the same paths as the first four beams but are subject to differing relative phase delays with respect to the relative phase delays of the beams from the first pulse so that an interference pattern is formed that is similar or identical to the initial interference pattern but which is shifted in spatial position relative to the initial pattern. To generate the necessary relative phase delays electro-optic phase modulators are provided on at least one of the four beam lines and are adjusted in the time interval between the first and second pulses. If a pulse from a frequency-tripled Nd:YAG laser of duration approximately 5ns is used, then a delay line of a few metres length gives enough delay to avoid overlap in time between the two exposures and to allow the phase modulators to change state between pulses.

Using any of the methods described above which employ the double exposure technique, the photosensitive material is subsequently developed, using conventional techniques, in the same manner as described previously. The double exposure technique enables the shape of a contour of constant dose within the photosensitive material to be accurately controlled which increases the ease of the design and fabrication of open yet continuously connected structures. Figure 4 is a diagram of an intensity contour, having fcc symmetry, produced using a double-pulse exposure with wavevectors different to those set out above and so having a smaller unit cell dimension of approximately $0.3\mu\text{m}$. The intensity contours shown in Figure 4 reveal a structure having very fine bonds and a low volume filling fraction.

As mentioned earlier, the photosensitive material may be irradiated with more than two exposures. As long as substantial photochemical changes do not occur in the total time during which irradiation takes place, it is possible to ensure that all exposures produce periodic intensity patterns with the same periodicity or commensurable periodicities. In the case where successive exposures correspond to irradiation with laser beams following the same paths, the relative phase delay between the beams is altered between each pulse from the source; this enables three or

more exposures of the material to be performed with each one producing an interference pattern spatially shifted with respect to the other interference patterns.

For many suitable photosensitive materials the duration of the exposure of the photosensitive material to electromagnetic radiation must be short enough that the intensity interference pattern is not significantly perturbed by photoinduced changes in the refractive index of the photosensitive material. Short pulse exposure reduces the constraints on the mechanical stability of the optical components. To ensure that the intensity interference pattern formed in the sample material is not significantly affected by changes in refractive index induced by irradiation, ideally the sample material should not be subjected to irradiation for more than 100 ms. With other photosensitive materials, major photoinduced changes in refractive index do not occur during exposure but during subsequent procedures, for example heating of the sample.

Using the method described above photosensitive material was irradiated with a single exposure from an injection-seeded, frequency-tripled Nd:YAG laser. The resultant 3-d periodic variations in samples of photosensitive material are shown in Figures 5, 6 and 7. In each case the single exposure lasted for approximately 6 ns and was selected using a mechanical shutter. The laser beam was split into four beams using three beam splitters and each beam was passed through a half wave plate and polariser to control the linear polarisation state and intensity of each of the beams. The diameter of each beam was approximately 8 mm and the four beams interfered in a sample of photosensitive material to produce a fcc periodic pattern (refraction at the air/sample interface means that the structure is not cubic but somewhat foreshortened in the direction perpendicular to this interface). The sample film was oriented in the (1,1,1) plane and the beam directions of propagation were as follows:

Beam	Direction of Propagation	Polarisation	Relative Pulse Energy
1	[1,1,1]	[-1,0,1]	5
2	[1,1,5]	[5,5,-2]	1
3	[1,5,1]	[-1,0,1]	1
4	[5,1,1]	[1,2,-7]	1

Figures 5a and 5b are atomic force microscopy images, at 6x6 micron, of the top and bottom surfaces respectively of a photosensitive material after irradiation as described above. The periodic structure is immediately visible from the images and the fact that the periodic structure is found on both the top and bottom surfaces is evidence of the coherence of the 3-D fcc optical pattern through the thickness of the sample material. In this experiment the sample material consisted of 80 parts by weight of Actilane™ 270 (a difunctional urethane acrylate oligomer supplied by Akros Chemicals); 20 parts by weight of PETA (pentaerythritol triacrylate); and 20 parts by weight of DMPA (2,2-dimethoxy-2-phenyl acetophenone, a photoinitiator also known as Irgacure™ 651). The sample material was spread in a 50 micron layer using a K-bar spreader. The laser energy was 286 mJ with pulse energies 50:10:10:10 mJ. After irradiation the sample material was developed by agitating the sample material in acetone for approximately 10 mins.

For Figure 6a the sample material consisted of 60 parts by weight of Actilane™ 320 (a difunctional epoxy acrylate oligomer supplied by Akros Chemicals) 40 parts by weight of PETA and 2 parts by weight of DMPA. In this experiment the sample material was spread in a 100 micron layer on a fused silica substrate again using a K-bar spreader. The laser energy was 300 mJ with pulse energies 65:13:13:13 mJ. After irradiation the sample material was developed for approximately 30 mins in a sonic bath with

acetone. To cleave the sample, the sample was cooled in liquid nitrogen and then snapped (not cut) to produce a cleaved plane clearly showing the terraces of the periodic structure in the irradiated sample. The atomic force microscopy image shown in Figure 6a is a 20x20 micron scan of the film edge after breaking. The presence of the terracing in the sample material further confirms the continuation of the periodic structure through the body of the sample material and the true 3-D nature of the periodic variation of refractive index in the photosensitive material after irradiation. In Figure 6b the dimensions of the cleaved edge are shown graphically. The step height is approximately 700 nm which is equal to the dimension of one unit cell of the optically created pattern.

In Figure 7 the Bragg diffraction pattern obtained from a third sample of photosensitive material is shown. In this case the sample material consisted of 50 parts by weight of Actilane™ 270, 50 parts by weight of PETA and 2 parts by weight of DMPA. The sample material was spread in a 50 micron layer using a K-bar spreader over a fused silica substrate. In this case the laser energy was 286 mJ with pulse energies 50:10:10:10 mJ and development of the sample material after irradiation was agitation in acetone for approximately 10 mins. To produce the experimental results shown in Figure 7 the 3-D microstructured photonic crystal material was rotated about an axis making an angle of approximately 15° with the

[1,0,-1] direction in the (1,1,1) plane of the fcc structure. A collimated beam of white light was incident on the photonic crystal material perpendicular to this axis; $\theta=0^\circ$ corresponds to incidence along the [1,1,1] direction. The points plotted show wavelengths at which strong Bragg scattering from the periodic structure leads to a minima in the transmitted intensity of the undeviated beam (measured by a spectrophotometer). The solid lines correspond to a calculation of the angular dependence of the wavelengths satisfying the Bragg scattering condition for various crystal planes.

The experimental results described above with reference to Figures 5, 6 and 7 show clearly how with the present method, 3-D periodic variations in refractive index in the form of 3-D periodic structures extending through the entire depth of the sample material can be produced.

5 The above methods may also be used to create photonic crystal structures incorporating intended defects. Such defects are useful either in the form of structural defects or through the introduction of isolated foreign matter, possibly having non-linear optical properties. Defects may be used to create and control electromagnetic modes within the photonic crystal
10 material for the purposes of creating waveguides or microcavities. Microcavities, in which emission of radiation is channelled into a small number of modes, may be used to control the direction of emission and increase the spectral brightness of radiation sources such as light emitting diodes. Microcavities may also be used to create lasers with low or zero
15 threshold densities of electrical or optical pumping. Other optical or electro-optical devices incorporating defects in a photonic crystal material are also envisaged.

Reference has been made in the above description generally to photosensitive materials. Suitable materials for use in the above methods
20 are acrylate negative photoresists; many analogous systems are also possible. Polyacrylates are transparent at 355nm; polymerisation is induced by conventional radical photoinitiators and proceeds in the dark following a pulsed exposure using radiation from a frequency tripled Nd:YAG laser with wavelength 355nm. Material with a high density of
25 photochemically induced cross-linking is rendered relatively insoluble and is retained during development. A suitable concentration of a radical inhibitor may be used to alter the threshold between insoluble irradiated regions and soluble regions or to increase the sharpness of this threshold. The major chemical change due to polymerisation occurs with an induction
30 period of several milliseconds, well after the exposure is complete. Hence, the duration of irradiation of the photosensitive material is preferably less than 1 millisecond, and ideally less than 100 ns. Photochemically induced

changes in refractive index will therefore not significantly affect a three-dimensional intensity pattern produced by the overlap of beams produced from a single pulse from a typical Nd:YAG laser with a pulse duration of approximately 6ns; the only significant chemical change which is likely to occur during such a laser pulse is the dissociation of the photoinitiator species. A 100mJ optical pulse can be used to polymerise a 1 cm² film and to produce a periodic intensity variation that is approximately independent of depth through a 100µm thickness film. It is believed that defects in the periodic structure as a result of crystal defects, volume changes through heat dissipation and strain will not significantly affect the ability of the material to act as a photonic crystal using the above described method.

An alternative materials system is a positive photoresist based on a copolymer of p-hydroxystyrene and t-butylacrylate. Absorption of ultraviolet light by a photoacid generator initiates a reaction in which the photoacid generator catalyses the deprotection of the t-butyl ester to give a carboxylic acid. When heated to 140°C ('post-exposure baking') approximately 200 carboxylic acid residues are created for each photon absorbed and the polymer becomes soluble in aqueous alkali. No swelling occurs and in conventional photolithography line resolutions of < 250nm can be routinely achieved. In this positive system it is the more-irradiated material that is removed by dissolution and the less-irradiated material that is retained to form a photonic crystal structure. Substantial changes in the refractive index of the sample will not occur until the post-exposure bake relaxing the condition that the sample material should not be subjected to irradiation for more than 100 ms.

Whilst the examples and methods described above can be used to directly produce photonic crystal material. The material produced by this method may also be used as a template for further fabrication steps to produce a photonic crystal material having a different refractive index to that of the sample material. As mentioned earlier, a material may be introduced into the voids between the residual material produced during the initial lithographic technique. Solid material may be introduced either by

solidification from a melt, or by chemical vapour deposition, or by electroplating, electro-deposition, chemical deposition or precipitation from solution, or by sedimentation or other techniques. The original developed material may then be removed using conventional techniques to create a
5 negative of the original lattice. Further iteration of these steps can be performed as necessary to obtain a lattice of material having the desired refractive index with the correct structure. It is believed that the refractive indexes of the photosensitive materials suitable for use with the methods described above are not capable of producing a photonic crystal material
10 having a complete photonic band gap, i.e. a frequency range that is forbidden for all directions of propagation. Therefore, the initial photonic crystal material produced by the above described methods will need to be used as a template in the manner outlined above to produce photonic crystal material having the desired refractive index.

15 Although in the detailed examples reference was made to coherent radiation sources, the method may alternatively employ partially coherent sources such as a discharge lamp. Also, although most applications of the method described above use a single laser source it is envisaged that multiple laser sources may be used. The radiation used in the method
20 described above having a wavelength of 355nm is in the ultraviolet spectral range, alternative wavelengths of electromagnetic radiation may be employed with both longer and shorter wavelengths where appropriate.

Although not mentioned above, it is envisaged that with a single source the beam of radiation is divided using partially reflective mirrors to
25 split the radiation by amplitude or by using optical components that reflect, diffract, refract or otherwise affect different parts of the wavefront from the source in different ways (division of amplitude). In addition, using the above method it is possible to fabricate three dimensional structures using more than four intersecting beams, and using radiation other than in the
30 form of collimated beams.

With the methods and examples described above, photonic crystals can be fabricated having a three dimensional periodic structure. Such

structures are useful as low-loss waveguides with tight curvature for on-chip signal routing. Also, by using the photonic crystal emission wavelengths can be controlled and the spectral brightness of light-emitting diodes improved. The photonic crystal may additionally be used to limit the

5 number of modes into which a laser may emit radiation thereby lowering the threshold current of the laser and the characteristic of photonic crystal to suppress spontaneous emission in a certain frequency band can be used to enhance photon number state squeezing which offers a reduction in bit-error rate in optical transmission. Further applications of the photonic

10 crystal produced in accordance with the described methods are envisaged for aesthetic as well as technical purposes.

CLAIMS

1. A method of forming a photonic crystal material comprising irradiating a sample of photosensitive material with electromagnetic radiation
5 propagating in different directions within the sample and generating a three dimensional periodic variation of the intensity of irradiation within the sample by interference between the electromagnetic radiation propagating in different directions whereby a three dimensional periodic variation in the refractive index of the photosensitive material is
10 produced based on the periodic variation of the intensity of irradiation.
2. A method as claimed in claim 1, wherein the irradiated sample of photosensitive material is developed to remove either more irradiated or less irradiated regions of the sample.
15
3. A method as claimed in claim 2, wherein material is introduced into the voids produced by development of the irradiated sample of photosensitive material.
- 20 4. A method as claimed in claim 3, wherein the optical properties of the irradiated sample are adjusted by the introduction of a material having a predetermined refractive index that is different to the refractive index of the photosensitive material remaining in the irradiated sample.
- 25 5. A method as claimed in claim 3, wherein the irradiated sample is used as a template for the production of other composite materials having periodic variations in refractive index.
- 30 6. A method as claimed in any one of the preceding claims, wherein the sample of photosensitive material is subjected to multiple exposures each exposure producing respective interference patterns within the sample.

7. A method as claimed in any one of the preceding claims, wherein the photosensitive material is irradiated for less than 100 ms.
- 5 8. A method as claimed in claim 7, wherein the photosensitive material is irradiated for less than 100 ns.
9. A method as claimed in any one of the preceding claims, wherein the sample of photosensitive material is irradiated with a coherent source of
- 10 electromagnetic radiation.
10. A method as claimed in claim 6, wherein the sample of photosensitive material is irradiated with a pulsed coherent source.
- 15 11. A method as claimed in any one of the preceding claims, wherein the three dimensional pattern within the sample is formed by directing electromagnetic radiation from at least four beams at the sample of photosensitive material so as to intersect and interfere within the sample.
- 20 12. A method as claimed in any one of the preceding claims, wherein the frequency of the incident radiation is selected in dependence on the desired length scale of the periodicity within the irradiated sample.
- 25 13. A photonic crystal material manufactured by the method as claimed in any one of the preceding claims.
14. A photonic crystal material as claimed in claim 13, wherein the photosensitive material is a positive resist.
- 30 15. A photonic crystal material as claimed in claim 14, wherein the photosensitive material includes a radical inhibitor.

16. A photonic crystal material having a three-dimensional periodicity at a sub-micron length scale of the refractive index.
- 5 17. A photonic crystal material as claimed in any one of claims 13 to 16, wherein the material has 3-D periodicity of its refractive index through a thickness of at least 10 micron.
- 10 18. A photonic crystal material as claimed in claim 17, wherein the material has 3-D periodicity of its refractive index through a thickness of at least 50 micron.

1/4




Figure 1




Figure 7

SUBSTITUTE SHEET (RULE 26)

2/4




Figure 2




Figure 3




Figure 4




Figure 5a




Figure 5b





Figure 6a



INTERNATIONAL SEARCH REPORT

Interr. Application No

PCT/GB 98/02462

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G02B6/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	BERGER V ET AL: "Photonic band gaps and holography" JOURNAL OF APPLIED PHYSICS, 1 JULY 1997, AIP, USA, vol. 82, no. 1, pages 60-64, XP002084653 ISSN 0021-8979 see the whole document	1-18
X	US 5 600 483 A (FAN SHANHUI ET AL) 4 February 1997 see column 2, line 56 - column 4, line 51; figure 1 --- -/--	16

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"S" document member of the same patent family

Date of the actual completion of the international search

17 November 1998

Date of mailing of the international search report

04/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lerbinger, K

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/GB 98/02462

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	BING-YING C ET AL: "CRYSTALLIZATION OF DIELECTRIC SPHERES IN LASER STANDING WAVE FIELD" ACTA PHYSICA SINICA, vol. 3, no. 11, November 1994, pages 861-869, XP000618222 see the whole document ---	1-12
A	DONGBIN MEI ET AL: "Three-dimensional ordered patterns by light interference" OPTICS LETTERS, 1 MARCH 1995, USA, vol. 20, no. 5, pages 429-431, XP002084654 ISSN 0146-9592 see the whole document ---	1-12
A	EP 0 624 558 A (HOECHST AG ; IMM INST MIKROTECH (DE)) 17 November 1994 see the whole document ---	5
A	DE 196 28 355 A (DEUTSCHE TELEKOM AG) 13 March 1997 see the whole document -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/02462

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5600483 A	04-02-1997	US 5440421 A WO 9530917 A	08-08-1995 16-11-1995
EP 0624558 A	17-11-1994	DE 4316184 A CN 1104616 A DE 59406949 D JP 7237210 A US 5698485 A	17-11-1994 05-07-1995 29-10-1998 12-09-1995 16-12-1997
DE 19628355 A	13-03-1997	AU 696469 B AU 7277996 A WO 9709643 A EP 0876631 A	10-09-1998 27-03-1997 13-03-1997 11-11-1998